



# HAG 08

## Technical Data Sheet

### Description:

Waterborne anticorrosive primer

### Usage:

Fast-drying acrylic primer and self-priming (2 in 1) coating for steel constructions, pallets, transport boxes, crates, wooden cottages, pergolas, arbours, summerhouses, fences, eaves, parapets, windows, ceilings, casing frames, barks, garden furniture. Can be used for coating of mechanically stressed floor and other mineral surfaces. Applicable by airless- or airmix-spraying, brush or roller. For application top-coats HAE 30 or HAE 34 wait 20 minutes, for application top-coats KD 53 or KD 54 wait 60 minutes. For higher hardness and faster drying apply the top-coat after 4 hours. Suitable for painting products in indirect contact with foodstuffs, animal feed and drinking water.

### Substrate:

Steel, new and old zinc, aluminium, wood, mineral surfaces (floors)

### Colours:

RAL 7035, VIT 0100, VIT 0110, VIT 0199, VIT 0841

### Specific gravity: (ČSN EN ISO 2811-1)

1,34 g/cm<sup>3</sup>

### Solids: (ČSN EN ISO 3251)

by weight 57 %

by volume 42 %

### Theoretical spreading rate: (ČSN EN ISO 23811)

undiluted paint			
40 µm DFT	7,8 m <sup>2</sup> /kg	10,5 m <sup>2</sup> /liter	128,4 g/m <sup>2</sup>
80 µm DFT	3,9 m <sup>2</sup> /kg	5,2 m <sup>2</sup> /liter	256,5 g/m <sup>2</sup>

To reach 40 µm DFT apply 95 µm undiluted paint. Practical spreading rate depends on application method and conditions, shape and roughness of the surface.

### Drying: (ČSN 673052)

120 µm WFT, temperature 23 ± 2°C, relative humidity 50 ± 5%, supply viscosity	surface dry (grade 1)	to touch (grade 3)	to manipulation (grade 4)
	20 minutes	35 minutes	60 minutes

Drying and recoatability time strongly depend on wet film thickness, temperature, humidity, ventilation and paint colour. Fully load and measure the coated film after 7 days, laboratory testing after 3 weeks of drying under the above conditions.

### Gloss: (ČSN ISO 2813)

Matt 9 GU, angle-wise 60°, supply viscosity

### Supply viscosity:

Thixotropic liquid unmeasurable by ISO outflow cup

VITON s.r.o.  
Třída Čs.armády 167  
391 81 Veselí nad Lužnicí  
Czech republic  
Issued: 10.11.2016



mobil: +42(0) 724 580 404  
tel: +42(0) 381 581 022  
objednavky@viton.cz  
www.viton.cz



# HAG 08

## Technical Data Sheet

### Recommended dilution: (ČSN 673032)

	airless	brush/roller
thinner	water	water
by weight	not dilute	2 %
by volume	not dilute	3 %

### Sagging: (ČSN EN ISO 16862)

temperature 23 ± 2°C, relative humidity 50 ± 5%	
supply viscosity	no sagging 350 µm WFT

### Application conditions:

The surface must be dry and properly ungreased. The air, surface and paint temperature cannot decrease below +10°C during application and drying. Relative humidity cannot exceed 70%. The surface temperature must be at least 3°C above the dew point. In cold weather, it is advisable to make one very thin coat first to dry quickly.

### Surface preparation:

Remove oil, grease, salt and other contamination from the surface with a suitable detergent according to ČSN EN ISO 12944-4. Use the highly effective ecological cleaner CL 07.

Steel surfaces: Abrasive blast-cleaning to Sa 2½, alternatively manual or mechanical cleaning to min. Sa 3 corresponding to ČSN EN ISO 8501-1. It is necessary to apply the paint in 2 layers, recommended dry film thickness (DFT) is 80-120 µm.

Galvanized surfaces: For reaching the required roughness use the sweeping method, e.g. using silica sand, alternatively mechanical sanding. At least clean the surface with a ecological cleaner CL 07. It is recommended to apply a diluted extra first coat on hot galvanized surfaces.

Aluminium surfaces: For reaching the required roughness use the sweeping method by a non-metallic abrasive, alternatively mechanical sanding. At least clean the surface with a ecological cleaner CL 07.

Previously painted surfaces: Remove oil, grease, salt and other contamination from the surface with a ecological cleaner CL 07, sanding of the surface recommended. Observe the compatibility of preceding and subsequent coats.

Wooden surfaces: The surface must be dry and cleaned of contamination, wax, grease, flaking and incoherent material. Fill cracks and holes with a stopper on wood. Sand all filled and glossy surfaces. Remove the residual dust by vacuum cleaning. In case of increased risks apply an insecticidal and an antifungal agent. As a renovation coating apply one or two layers of paint, as a priming coat of uncoated wood apply two or three layers according to the structure of wood. For reaching the highest quality gently sand the surface with a sandpaper Nr. 240 after every coat.

Mineral surfaces: Remove oil, grease, salt and other contamination from the surface with a suitable detergent, sanding or blast cleaning as needed. Remove the residual grit by brushing or vacuum cleaning. Use RK 975 STOPPER for touch-up repairs, leveling and smoothing of the surface. In case of highly strained systems it is necessary to test the solidity of the mineral surface. Observe the compatibility of preceding and subsequent paints when renovating previously painted surfaces.

### Application method:

Spray guns, brush, roller. For airless spraying use the nozzle orifice of Ø 0.011" - 0.021", nozzle pressure: 120 - 180 bar, adjust the angle of application to the shape of the surface. For spraying use the nozzle orifice of 1.5 - 2 mm, nozzle pressure: 3 - 4 bar. For application by brush/roller select appropriate equipment according to the paint type and viscosity.

VITON s.r.o.  
Třída Čs.armády 167  
391 81 Veselí nad Lužnicí  
Czech republic  
Issued: 10.11.2016



mobil: +42(0) 724 580 404  
tel: +42(0) 381 581 022  
objednavky@viton.cz  
www.viton.cz



# HAG 08

## Technical Data Sheet

### Storage:

In the original unopened packaging at temperatures between +5°C and +25°C. Cannot freeze!

### Shelf life:

24 months

### Packaging in kg:

0,7; 3,5; 12; 24; 1000

### Notes:

DFT - dry film thickness  
WFT - wet film thickness

MS - medium dry matter  
HS - high dry matter

GU - Gloss Unit  
KU - Krebs unit of viscosity

All information given in this technical data sheet are based on our best knowledge, laboratory test results and practical experience to the date specified below. According to the fact that the conditions of the product's use are out of our control, we can only guarantee the product quality itself. As a producer we cannot be responsible for damage arising from the use of the products without following above recommended instructions or for improper purposes. We reserve the right to change above specified information without prior notice. Always request the actual version of the product data sheet. This technical data sheet replaces all previously released. The validity of the data provided here will be terminated automatically after five years.

