



KE 53

Technical Data Sheet

Description:

Self-priming alkyd-urethane paint 3in1

Usage:

Alkyd-urethane primer and top-coat (3 in 1) universally applicable on small or large areas. Suitable for interior or exterior coatings of steel constructions, pallets, conveyors, containers, transport boxes, window sills, railings, roofs, windows and doors without a priming coat. The advantage of urethaneized binder is higher color fastness, UV-durability and mechanical resistance. It can be applied by airless- or airmix-spraying, by a roller or a brush. The second layer of KE 53 can be applied 40 minutes after the first layer, for brush/roller is recommended apply the second layer after 12 hours.

Substrate:

Steel, wood

Colours:

RAL, VIT

Specific gravity: (ČSN EN ISO 2811-1)

1,30 g/cm³

Solids: (ČSN EN ISO 3251)

by weight 67 %

by volume 50 %

Theoretical spreading rate: (ČSN EN ISO 23811)

undiluted paint			
40 µm DFT	9,6 m ² /kg	12,5 m ² /liter	104,0 g/m ²
80 µm DFT	4,8 m ² /kg	6,3 m ² /liter	208,0 g/m ²

To reach 40 µm DFT apply 80 µm undiluted paint. Practical spreading rate depends on application method and conditions, shape and roughness of the surface.

Drying: (ČSN 673052)

120 µm WFT, temperature 23 ± 2°C, relative humidity 50 ± 5%, outflow time 60s, ISO outflow cup 6 mm	surface dry (grade 1)	to touch (grade 3)	to manipulation (grade 4)
	40 minutes	3 hours	4 hours

Drying and recoatability time strongly depend on wet film thickness, temperature, humidity, ventilation and paint colour. Fully load and measure the coated film after 7 days, laboratory testing after 3 weeks of drying under the above conditions.

Gloss: (ČSN ISO 2813)

Semi-gloss 50 GU, angle-wise 60°, outflow time 60s, ISO outflow cup 6 mm

Supply viscosity:

Thixotropic liquid unmeasurable by ISO outflow cup type

VITON s.r.o.
Planá 90
370 01 České Budějovice
Czech republic
Issued: 2.7.2021



mobil: +42(0) 724 580 404
tel: +42(0) 381 581 022
objednavky@viton.cz
www.viton.cz



KE 53

Technical Data Sheet

Recommended dilution: (ČSN 673032)

	airless	brush/roller
thinner	KT 01	KT 04
by weight	5 %	7 %
by volume	8 %	11 %

Sagging: (ČSN EN ISO 16862)

temperature 23 ± 2°C, relative humidity 50 ± 5%	
outflow time 60s, ISO outflow cup 6 mm	no sagging 350 µm WFT

Application conditions:

The surface must be dry. The air, surface and paint temperature cannot decrease below +5°C during application and drying. Relative humidity cannot exceed 80%. The surface temperature must be at least 3°C above the dew point.

Surface preparation:

Remove oil, grease, salt and other contamination from the surface with a suitable detergent according to ČSN EN ISO 12944-4.

Steel surfaces: Abrasive blast-cleaning to Sa 2½, alternatively manual or mechanical cleaning to min. St 3 corresponding to ČSN EN ISO 8501-1.

Previously painted surfaces: Remove oil, grease, salt and other contamination from the surface with a suitable detergent, sanding of the surface recommended. Repair all damage to the coating with an anticorrosive primer. Observe the compatibility of preceding and subsequent coats.

Wooden surfaces: The surface must be dry and cleaned of contamination, wax, grease, flaking and incoherent material. Fill cracks and holes with a stopper on wood. Sand all filled and glossy surfaces. Remove the residual dust by vacuum cleaning. In case of increased risks apply an insecticidal and an antifungal agent. As a renovation coating apply one or two layers of paint, as a priming coat of uncoated wood apply two or three layers according to the structure of wood. For reaching the highest quality gently sand the surface with a sandpaper Nr. 240 after every coat.

Application method:

Airless spraying, airmix spraying, brush or roller. For airless spraying use the nozzle orifice of Ø 0.011" - 0.021", nozzle pressure: 120 - 180 bar, adjust the angle of application to the shape of the surface. For airmix spraying use the nozzle orifice of 1.5 - 2 mm, nozzle pressure: 3 - 4 bar. For application by brush/roller select appropriate equipment according to the paint type and viscosity.

Storage:

in the original unopened packaging at temperatures between +5°C and +25°C.

Packaging in kg:

10; 25

Packaging of base 0100 in kg:

9,8; 24,5

Packaging of base 0000 in kg:

8; 20

VITON s.r.o.
Planá 90
370 01 České Budějovice
Czech republic
Issued: 2.7.2021



mobil: +42(0) 724 580 404
tel: +42(0) 381 581 022
objednavky@viton.cz
www.viton.cz



KE 53

Technical Data Sheet

Notes:

DFT - dry film thickness
WFT - wet film thickness

MS - medium dry matter
HS - high dry matter

GU - Gloss Unit
KU - Krebs unit of viscosity

All information given in this technical data sheet are based on our best knowledge, laboratory test results and practical experience to the date specified below. According to the fact that the conditions of the product's use are out of our control, we can only guarantee the product quality itself. As a producer we cannot be responsible for damage arising from the use of the products without following above recommended instructions or for improper purposes. We reserve the right to change above specified information without prior notice. Always request the actual version of the product data sheet. This technical data sheet replaces all previously released. The validity of the data provided here will be terminated automatically after five years.

