

Technical Data Sheet

Description:

Synthetic thinner for airless- or airmix-spraying

Usage:

KT 01 is intended to adjust the viscosity of VITON paints applied by a spray gun. The quantity of thinner depends on the chosen type of application, on the temperature and on the type of chosen paint. The maximal quantity is specified in the technical data sheet of the particular paint. Mentioned thinner is intended only for coating materials and paints by VITON s.r.o. When applying a VITON paint combined with a thinner by another manufacturer the paint guarantee expires.

Colours:

0000 - colourless

Specific gravity: (ČSN EN ISO 2811-1)

0,82 g/cm³

Application conditions:

Particular paint mix from the bottom. Add the recommended amount of thinner and mix well. If the sprayed surface is not smooth after application or if brush or roller are noticeably visible, add more thinner. Observe the maximum dosage of thinner prescribed for the selected application method. In the case of overdose, the paint loses the cover and causes excessive environmental damage. Do not apply the coatings in direct sunlight, during a wet and rainy day, early morning or late afternoon. This reduces the quality of paint and reduces its life.

Storage:

in the original unopened packaging at temperatures between +5°C and +25°C.

Packaging in l:

0,5; 1; 4; 9; 30; 190

Notes:

DFT - dry film thickness
WFT - wet film thickness

MS - medium dry matter
HS - high dry matter

GU - Gloss Unit
KU - Krebs unit of viscosity

All information given in this technical data sheet are based on our best knowledge, laboratory test results and practical experience to the date specified below. According to the fact that the conditions of the product's use are out of our control, we can only guarantee the product quality itself. As a producer we cannot be responsible for damage arising from the use of the products without following above recommended instructions or for improper purposes. We reserve the right to change above specified information without prior notice. Always request the actual version of the product data sheet. This technical data sheet replaces all previously released. The validity of the data provided here will be terminated automatically after five years.