



# S 2013

## Technical Data Sheet

### Description:

Self-priming alkyd-urethane paint 3in1

### Usage:

High-quality alkyd-urethane primer and top-coat (3 in 1) universally applicable on small or large areas. Suitable for interior or exterior coatings of fences, window sills, eaves, railings, agriculture machinery, cottages, garden furniture and wood without a priming coat. The advantage of urethaneized binder is higher color fastness, UV-durability and mechanical resistance. It can be applied by airless- or airmix-spraying, by a roller or a brush. The second layer of S 2013 can be applied 90 minutes after the first layer, for brush/roller is recommended apply the second layer after 20 hours.

### Substrate:

Steel, wood

### Colours:

RAL, VIT

### Specific gravity: ( SN EN ISO 2811-1)

1,24 g/cm<sup>3</sup>

### Solids: ( SN EN ISO 3251)

by weight 67 ± 2 %

by volume 52 ± 2 %

### Theoretical spreading rate: ( SN EN ISO 23811)

| undiluted paint |                         |                            |                        |
|-----------------|-------------------------|----------------------------|------------------------|
| 40 µm DFT       | 10,6 m <sup>2</sup> /kg | 13,1 m <sup>2</sup> /liter | 94,6 g/m <sup>2</sup>  |
| 80 µm DFT       | 5,3 m <sup>2</sup> /kg  | 6,6 m <sup>2</sup> /liter  | 189,3 g/m <sup>2</sup> |

To reach 40 µm DFT apply 77 µm undiluted paint. Practical spreading rate depends on application method and conditions, shape and roughness of the surface.

### Drying: ( SN 673052)

| 120 µm WFT, temperature 23 ± 2°C,<br>relative humidity 50 ± 5%, outflow time<br>60s, ISO outflow cup 6 mm | surface dry (grade 1) | to touch (grade 3) | to manipulation (grade 4) |
|---|-----------------------|--------------------|---------------------------|
|   | 3 hours               | 4 hours            | 7 hours                   |

Drying and recoatability time strongly depend on wet film thickness, temperature, humidity, ventilation and paint colour. Fully load and measure the coated film after 7 days, laboratory testing after 3 weeks of drying under the above conditions.

### Gloss: ( SN ISO 2813)

Gloss 80 GU, angle-wise 60°, outflow time 60s, ISO outflow cup 6 mm

### Supply viscosity:

Thixotropic liquid unmeasurable by ISO outflow cup type

VITON s.r.o.  
Planá 90  
370 01 eské Bud jovice  
Czech republic  
Issued: 27.10.2021



mobil: +42(0) 724 580 404  
tel: +42(0) 381 581 022  
objednavky@viton.cz  
www.viton.cz

## Technical Data Sheet

Recommended dilution: ( SN 673032)

|           |         |              |
|-----------|---------|--------------|
|           | airless | brush/roller |
| thinner   | KT 01   | KT 04        |
| by weight | 8 %     | 10 %         |
| by volume | 12 %    | 17 %         |

Sagging: ( SN EN ISO 16862)

|   |                                  |
|---|----------------------------------|
| temperature $23 \pm 2^{\circ}\text{C}$ , relative humidity $50 \pm 5\%$ |                                  |
| outflow time 60s, ISO outflow cup 6 mm                                  | no sagging 150 $\mu\text{m}$ WFT |

### Application conditions:

The surface must be dry. The air, surface and paint temperature cannot decrease below  $+5^{\circ}\text{C}$  during application and drying. Relative humidity cannot exceed 80%. The surface temperature must be at least  $3^{\circ}\text{C}$  above the dew point.

### Surface preparation:

Remove oil, grease, salt and other contamination from the surface with a suitable detergent according to SN EN ISO 12944-4.

Steel surfaces: Appropriate recommended priming coat necessary. This coating material is not intended for a direct application on this type of surface.

Galvanized substrate: Appropriate recommended priming coat necessary. This coating material is not intended for a direct application on this type of surface.

Aluminium substrate: Appropriate recommended priming coat necessary. This coating material is not intended for a direct application on this type of surface.

Previously painted surfaces: Remove oil, grease, salt and other contamination from the surface with a suitable detergent, sanding of the surface recommended. Repair all damage to the coating with an anticorrosive primer. Observe the compatibility of preceding and subsequent coats.

Wooden surfaces: The surface must be dry and cleaned of contamination, wax, grease, flaking and incoherent material. Fill cracks and holes with a stopper on wood. Sand all filled and glossy surfaces. Remove the residual dust by vacuum cleaning. In case of increased risks apply an insecticidal and an antifungal agent. As a renovation coating apply one or two layers of paint, as a priming coat of uncoated wood apply two or three layers according to the structure of wood. For reaching the highest quality gently sand the surface with a sandpaper Nr. 240 after every coat.

### Application method:

Airless spraying, airmix spraying, brush or roller.. For airless spraying use the nozzle orifice of  $0.011'' - 0.021''$ , nozzle pressure: 120 - 180 bar, adjust the angle of application to the shape of the surface. For airmix spraying use the nozzle orifice of 1.5 - 2 mm, nozzle pressure: 3 - 4 bar. For application by brush/roller select appropriate equipment according to the paint type and viscosity.

### Storage:

in the original unopened packaging at temperatures between  $+5^{\circ}\text{C}$  and  $+25^{\circ}\text{C}$ .



# S 2013

## Technical Data Sheet

### Packaging in kg:

0,7; 3,5; 10

### Packaging of base 0100 in kg:

0,686; 3,43; 9,8

### Packaging of base 0000 in kg:

0,56; 2,8; 8; 240

### Notes:

DFT - dry film thickness  
WFT - wet film thickness

MS - medium dry matter  
HS - high dry matter

GU - Gloss Unit  
KU - Krebs unit of viscosity

All information given in this technical data sheet are based on our best knowledge, laboratory test results and practical experience to the date specified below. According to the fact that the conditions of the product's use are out of our control, we can only guarantee the product quality itself. As a producer we cannot be responsible for damage arising from the use of the products without following above recommended instructions or for improper purposes. We reserve the right to change above specified information without prior notice. Always request the actual version of the product data sheet. This technical data sheet replaces all previously released. The validity of the data provided here will be terminated automatically after five years.

