



VIR.ES

Technical Data Sheet

Description:

Conductive agent for the vitocolormix® tinting system.

Usage:

Developed especially for regional dealers and wholesale to modification of coating materials according to the supplied recipes. The agent allow to adjust conductivity of coating material quickly and comfortably. Dose to the tinted coating material. Recommended dosage is 6 - 12 grams for 1 kilogram of coating material. After dosage mix well and measure the conductivity. Do not use for epoxy and waterborne coatings!

Colours:

0000 - bezbarvý, nažloutlý

Specific gravity: (ČSN EN ISO 2811-1)

0,95 g/cm³

Application conditions:

Conductive agent is intended only for using in combination with VITON coatings. It cannot be used as a separate coating material.

Storage:

in the original unopened packaging at temperatures between +5°C and +25°C.

Shelf life:

12 months

Packaging in kg:

0,8; 8

Notes:

DFT - dry film thickness
WFT - wet film thickness

MS - medium dry matter
HS - high dry matter

GU - Gloss Unit
KU - Krebs unit of viscosity

All information given in this technical data sheet are based on our best knowledge, laboratory test results and practical experience to the date specified below. According to the fact that the conditions of the product's use are out of our control, we can only guarantee the product quality itself. As a producer we cannot be responsible for damage arising from the use of the products without following above recommended instructions or for improper purposes. We reserve the right to change above specified information without prior notice. Always request the actual version of the product data sheet. This technical data sheet replaces all previously released. The validity of the data provided here will be terminated automatically after five years.

